

Illusion collection

Technical Specifications



Composition	Unit	Value
PU	%	1
Polyester	%	18
PVC	%	81
Total Weight	gr/m2	550
Total Thickness	mm	1
Tear Strenght	N	> 104
Width	Cm	1,4
Martindale Abrasion	Cycles	>40000
Color Fastness to Light	bw	>4
Flammability, Burning rate	N	PASS Bs585 I Part I
Determination Phthalates	N	PASS EN14372:2004

CLEANING

Weekly take care to get rid of any dust from the surface with a moist or soapy white, soft cotton cloth, and then rinse and dry out perfectly.

Visible and loose dirt should be picked up with a very soft broom or vacuum cleaner.

(DO NOT use any hard brush type vacuum on leather.)

NOTE

Due to dying process, some colors could present slightly difference between the col. swatch display on the catalogue, and the one expected.

MAJORFE, appeal for YOUR revalidation of the col. Exhibit on the catalogue, in result of eventuality failures in the elaboration of the catalogues.

Certain clothing and accessories dyes (such as those used in denim jeans), may migrate to lighter colors. This phenomenon is increase by humidity and temperature, and is irreversible. MAJORFE, will not assume responsibility for the dye transfer caused by external contaminants and possible permanent staining caused by this phenomenon.

SEDE

Rua do Padrão, 39
4580-493 Lordelo • Paredes • Portugal
T. 00351 224 447 600 • T. 00351 919 288 210
Fax 00351 224 449 308
Skype: majorfe.pt

encomendas@majorfe.com

ESPUMAS

Rua Monte Alto, 285
4585-460 Rebordosa
Paredes • Portugal
T. 00351 224 154 564
T. 00351 918 778 871

espumas@majorfe.com



www.majorfe.com